

# **CEME SUPER PLASTICIZER – 908**

Ultra High Range Water Reducer & Retarding, Concrete Admixture.

#### **Description:-**

Ceme Super Plasticizer SP-908 is an ultra-high range and retarding admixture for concrete. SP-908 is a polycarbo ether polymer based that improves cement dispersion by the action of conventional electrostatic dispersion forces, it's highly flowable without adding extra water.

#### **Benefits:-**

- Increases Flexure strength
- High early and 28 days' strength if advantage water reduction is taken
- Retains the initial work ability for longer time
- Cost effective
- Improves cohesion thus aids pumping of concrete
- High water reduction is possible
- Chloride free
- Reduce the incidence of honeycombing
- Produce high strength and flowing concrete without adding extra cement.
- Ideal with high grade of concrete mix
- Improves trowel ability & surface finish
- Reduction of 20% water cement ratio

## **Technical Data:-**


ТҮРЕ	G-Туре
Color	Brown
Color Chloride content	Nil
to BS5075 :1982	
Nitrate content	Nil
Consumption with	1.0 % to 1.50%
100kg cement	
Specific gravity	1.16 - 1.18 @ 25 °C
Air contents	Less than 1%
Freezing point	0°C. can be reconstituted, if
÷.	stirred after thawing
Flash point	None


## **Fields of Application:-**

- Micro silica concrete.
- Pre-cast concrete manufacture.
- Ready mix concrete.
- Long distance transportation.
- In hot weather to extend workability.
- Bridges and cantilever structures.
- Pre-stressed concrete.
- Floor slabs.
- Foundations.
- Walls and columns.
- Beams and slabs.

• For fair face results ADMIXTURE SPECIAL ADMIXTURE SURFACE IMPROVEMENT SHOTCRETE GROUTS WATER PROOFING FLOORING COATING JOINT SEALANT REPAIR CRACK INJECTION TILING High range water reducing & retarding super plasticizer.

\*results given are of laboratory it may vary at site due other materials.







## **Compatibility:-**

Ceme Super Plasticizer SP-908 is compatible with all type of cement complying with international standards. It can be used in combination with the following admixture additives, Waterproofing admixture **CEMETONE RMW.** 

## Standards:-

- BS-5075 Part 1.
- Packaging: Available on Empty Canes & Drums.
- Storage: Dry, Frost Free out of Direct sunlight.
- **Shelf Life:** 12 Months when storage in covered area.

## **Direction of Use:-**

## **Setting Time:-**

Ceme Super Plasticizer SP-908 ensures that rheoplastic concrete remains workable in excess 3 hours at+20°C. Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot and dry climates.

# Effect of Over Dosage:-

- Retardation of initial set
- Increase in air contents
- Increase in workability

## Mixing:-

Ceme Super Plasticizer SP-908 should be added to concrete during mixing cycle at same time as the water and aggregates. Never add Ceme Super Plasticizer SP-908 to the dry cement.

## Dispensing:-

Ceme Super Plasticizer SP-908 is introduced into the mixer together with mixing water. The plasticizing effect or water reduction is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of Ceme Super Plasticizer SP-908 to dry aggregate or cement is not recommended.

## Curing:-

Fresh poured concrete must be cured properly, particular at high temperatures in order to prevent plastic and drying shrinkages and cracks. Use CEME Curing Compounds to achieve best results or apply wet hessians.

# CAUTION:-

Ceme Super Plasticizer SP-908 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet

